

VECHO ACOUSTIC PANEL

FIRE CLASSIFICATION TEST

Test Report

No. AJFS2107005914FF

Date: JUL.28, 2021

PT. MITRA TIMUR LESTARI, HIGHPOINT

Jalan Daan Mogot Km 12 No. 55, Cengkareng Timur, Jakarta Barat 11730 Indonesia

Sample Name: 100% POLYESTER FIBER ACOUSTIC PANEL

SGS Ref No.: NBIN2107008309ML

Style/Item No.: /

Spec.: THICKNESS: 12mm

The above sample(s) was / were submitted and identified on behalf of the client. SGS is not responsible for the authenticity, integrity and results of the data and information and / or the validity of the conclusion arising therefrom. Results apply to the sample as received.

Test Requested:

EN 13501-1:2018 Fire classification of construction products and building elements—Part 1: Classification using data from reaction to fire tests.

Test Results: -- See attached sheet --

Test Period:

Sample Receiving Date : JUL.12, 2021

Test Performing Date : JUL.12, 2021 TO JUL.26, 2021

Signed for and on behalf of
SGS-CSTC Standards Technical Services Co., Ltd. Anji Branch



Allen Zou
Approved Signatory

I. Test conducted

This test is conducted as per EN 13501-1:2018 Fire classification of construction products and building elements — Part 1: Classification using data from reaction to fire tests. And the test methods as following:

1. EN 13823:2020 Reaction to fire tests for building products - Building products excluding floorings exposed to the thermal attack by a single burning item.
2. EN ISO 11925-2:2020 Reaction to fire tests — Ignitability of products subjected to direct impingement of flame — Part 2: Single-flame source test.

II. Details of classified product

a) Nature and end use application

The product “Acoustic panel” is defined as a decorative sheet. Its classification is valid for the following end use application: Interior Decoration, Interior Acoustic.

b) Description

Description	Acoustic panel
Color	White
Sample size	EN 13823: 1500mm×1000mm & 1500mm×495mm EN ISO 11925-2: 250mm×90mm
Thickness	12mm
Bulk Density	136 kg/m ³
Exposed surface	The front face

Mounting and fixing:

Calcium silicate board, with its density approximate 900kg/m³, thickness approximate 9mm, is as the substrate. The test specimens are fixed mechanically to the substrate. No joint in the specimens.

III. Test results

Test method	Parameter	Number of tests	Results
EN 13823	FIGRA _{0.2MJ} (W/s)	3	48.6
	FIGRA _{0.4MJ} (W/s)		48.6
	Whether lateral flame spread (LFS) to the edge of specimen (Yes/No)		No
	THR _{600s} (MJ)		5.0
	SMOGRA (m ² /s ²)		14.3
	TSP _{600s} (m ²)		45.2
	Flaming particles or droplets (Yes/No)		No

Test method	Parameter	Number of tests	Results
EN ISO 11925-2 Exposure = 30 s	Whether vertical flame spread (Fs) in excess of 150 mm within 60s (Yes/No)	6	No
	Ignition of the filter paper (Yes/No)		No

IV. Classification and field of application

a) Reference of classification

This classification has been carried out in accordance with **EN 13501-1:2018**.

b) Classification

The product, Acoustic panel, in relation to its reaction to fire behaviour is classified:

Fire behaviour		Smoke production			Flaming droplets	
B	—	s	1	,	d	0

Reaction to fire classification: B—s1, d0

Remark: The classes with their corresponding fire performance are given in annex A.

c) Field of application

This classification is valid for the following end use applications:

- With all substrates classified as A1 and A2
- With mechanically fixing
- No joint

This classification is valid for the following product parameters:

- Characteristics as described in section II b) of this test reports.

Statement:

This declaration of conformity is only based on the result of this laboratory activity, the impact of the uncertainty of the results was not included.

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Warning:

This classification report does not represent type approval or certification of the product.

The test laboratory has, therefore, play no part in sampling the product for the test, although it holds appropriate references to the manufacturer's factory production control that is aimed to be relevant to the samples tested and that will provide for their traceability.

Annex A

Classes of reaction to fire performance for construction products excluding floorings and linear pipe thermal insulation products

Class	Test method(s)	Classification criteria	Additional classification
A1	EN ISO 1182 ^a and	$T 30$, and $m 50\%$, and $t_f=0$ (i.e. no sustained flaming)	-
	EN ISO 1716	$PCS 2.0MJ/kg$ ^a and $PCS 2.0MJ/kg$ ^{b c} and $PCS 1.4MJ/m^2$ ^d and $PCS 2.0MJ/kg$ ^e	-
A2	EN ISO 1182 ^a or	and $T 50$, and $m 50\%$, and $t_f 20$ s	-
	EN ISO 1716		-
	EN 13823	$FIGRA 120W/s$ and $LFS < edge of specimen$ and $THR_{600s} 7.5MJ$	Smoke production ^f and Flaming droplets/particles ^g
B	EN 13823 and	$FIGRA 120W/s$ and $LFS < edge of specimen$ and $THR_{600s} 7.5MJ$	Smoke production ^f and Flaming droplets/particles ^g
	EN ISO 11925-2 ⁱ Exposure =30s	within 60s $F_s 150mm$	
C	EN 13823 and	$FIGRA 250W/s$ and $LFS < edge of specimen$ and $THR_{600s} 15MJ$	Smoke production ^f and Flaming droplets/particles ^g
	EN ISO 11925-2 ⁱ Exposure=30s	$F_s 150mm$ within 60 s	
D	EN 13823 and	$FIGRA 750W/s$	Smoke production ^f and Flaming droplets/particles ^g
	EN ISO 11925-2 ⁱ Exposure=30s	$F_s 150mm$ within 60 s	
E	EN ISO 11925-2 ⁱ Exposure =15s	$F_s 150mm$ within 20 s	flaming droplets/particles ^h

F	EN ISO 11925-2 ⁱ Exposure = 15 s	$F_s > 150\text{mm}$ within 20 s
<p>^a For homogeneous products and substantial components of non-homogeneous products. ^b For any external non-substantial component of non-homogeneous products. ^c Alternatively, any external non-substantial component having a PCS 2,0 MJ/m², provided that the product satisfies the following criteria of EN 13823: FIGRA 20 W/s, and LFS < edge of specimen, and THR_{600s} 4,0 MJ, and s1, and d0. ^d For any internal non-substantial component of non-homogeneous products. ^e For the product as a whole. ^f s1 = SMOGRA 30m²/s² and TSP_{600s} 50m²; s2 = SMOGRA 180m²/s² and TSP_{600s} 200m²; s3 = not s1 or s2 ^g d0 = No flaming droplets/ particles in EN 13823 within 600 s; d1 = no flaming droplets/ particles persisting longer than 10 s in EN 13823 within 600 s; d2 = not d0 or d1. Ignition of the paper in EN ISO 11925-2 results in a d2 classification. ^h Pass = no ignition of the paper (no classification); Fail = ignition of the paper (d2 classification). ⁱ Under conditions of surface flame attack and, if appropriate to the end-use application of the product, edge flame attack.</p>		



SGS authenticate the photo on original report only

End of Report